



1994

# BCT BEARING PLATE

## FPB01

SHEET NO.	REF. NO.
1 of 2	F-36-79

### **SPECIFICATIONS**

Bearing plate shall be formed from AASHTO M270M (ASTM A709M) Grade 250 steel plate and zinc-coated according to AASHTO M111 (ASTM A123) except when corrosion resistant steel is requested. No punching, drilling or cutting is permitted after the plate is zinc-coated. Where corrosion-resistant steel is desired, the plate shall be manufactured from AASHTO M270M (ASTM A709M) Grade 50W plate and shall not be painted or zinc-coated.

Dimensional tolerances not shown or implied are intended to be those consistent with the proper functioning of the part, including its appearance and accepted manufacturing practices.

### **INTENDED USE**

FPB01 Bearing Plates are used in various End Treatment/Terminal systems.

## **BCT BEARING PLATE**

**FPB01**

SHEET NO.

DATE

2 of 2

1995